# 3D

## **ABS Filament**

- High performance Acrylonitrile Butadiene Styrene (ABS) for material extrusion (ME)
- High rigidity, high gloss, medium impact strength
- Resistant to grease
- Good post-printing workability
- Strong odour during printing
- Main applications: Concept modelling for building, electrical, automotive industry etc. Non-critical parts such as enclosures.



### **Filament Specifications**

Size	Ø tolerance	Length
1.75mm	± 0.05mm	396 m
2.85mm	± 0.09mm	149 m
Material properties		

Description	Test method	Typical value
Density	ISO 1183	1.05 g/cm
Viscat softening temperature	ISO 306	104°C
Flexural strength	ISO 178	76 MPa
Flexural modulus	ISO 178	2200 Mpa
Impact strength - Charpy method 23°C	ISO 179	21 kJ/m2
Tensile strength	ISO 527	47 Mpa
Tensile elongation	ISO 527	30%

### Recommended printer set up

Extrusion temperature	250±10°C
Bed temperature	90°C
Printing speed	30 mm/s



# 3D

## **ABS Filament**

#### **Filaments Available**

Colour	Part Number	RAL code	PANTONE® ref.*	Diameter	Weight
Black	55026	9017	Black Process	1.75 mm	1 kg
White	55027	9003	White Process	1.75 mm	1 kg
Blue	55029	5002	PMS 2147C	1.75 mm	1 kg
Red	55030	3020	TBC	1.75 mm	1 kg
Green	55031	6018	TBC	1.75 mm	1 kg
Natural Transparent	55028	-	N/A	1.75 mm	1 kg
Silver/Metal Grey	55032	9006	TBC	1.75 mm	1 kg
White	55034	9003	White Process	2.85 mm	1 kg
Black	55033	9017	Black Process	2.85 mm	1 kg
Natural Transparent	55035	-	N/A	2.85 mm	1 kg
Silver	55036	9006	TBC	2.85 mm	1 k

#### \* Closest PANTONE® colour reference

Verbatim filament is manufactured from high quality materials to extremely rigid standards. The filaments are manufactured from the highest quality materials and produced to extremely tight tolerances to ensure consistent feed and stable printing. The filaments are distributed in vacuum-sealed bags with desiccant, and wound onto a custom spool that has been designed for strength, uniform dynamic performance and trouble-free dispensing.

